

# Product Datasheet



## BU Powder Coatings

**AkzoNobel**  
Tomorrow's Answers Today

### Interpon 610 AM

The information given in this datasheet is generic for the range **Interpon 610 AM**. Specific products within the range can vary from the generic. For these products individual product datasheets are available

**Product Description** **Interpon 610 AM** is a series of polyester based powder coatings, formulated without the use of TGIC, designed for the exterior environment, offering the benefits of **Interpon 610** in combination with specific antibacterial activity.

**Interpon 610 AM** powders are available in a wide range of colours in gloss, reduced gloss, textured and other special finishes or can be custom matched to the user's requirements.

<b>Powder Properties</b>	<b>Chemical type</b>	Polyester
	<b>Particle Size</b>	Suitable for electrostatic spray
	<b>Specific gravity</b>	1.2-1.7 g/cm <sup>3</sup> depending on colour
	<b>Storage</b>	Dry cool conditions below 25°C
	<b>Shelf life</b>	12 months
	<b>Sales Code</b>	M-series
	<b>Stoving schedule<sup>(a)</sup></b> (object temperature)	15 minutes at 190°C 10 minutes at 200°C 8 minutes at 210°C

a) For high reactivity (HR) powders see overleaf

**Test Conditions** The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

<b>Substrate</b>	Mechanical tests: Gold Seal polished steel Chemical & durability tests: Gold Seal lightweight
<b>Pretreatment</b>	Zinc phosphate
<b>Film Thickness</b>	60 - 70 microns
<b>Stoving</b>	5 minutes at 200°C (object temperature)

<b>Mechanical Tests</b>	<b>Flexibility</b>	ISO6860 (Conical Mandrel)	Pass 3mm
	<b>Adhesion</b>	ISO2409 (2mm Crosshatch)	Gt 0
	<b>Erichsen Cupping</b>	ISO1520	Pass >7mm
	<b>Hardness</b>	ISO1518 (4000gms)	Pass - no penetration to substrate
	<b>Impact</b>	ASTM D2794	Pass 25Kgcm direct and reverse

<b>Chemical and Durability Tests</b>	<b>Salt Spray</b>	ASTM B117 (250 hours)	Pass - no corrosion creep more than 2mm from scribe
	<b>Constant Humidity</b>	ISO6270-1 :1998(E) (240 hours)	Pass - no blistering or loss of gloss
	<b>Distilled Water Immersion</b>	ISO2812 (240 hours)	Pass - no blistering or loss of gloss
	<b>Exterior Durability</b>	Excellent - no chalking, slight loss of gloss after 12 months continuous exposure but no film breakdown or reduction in protective properties.	
	<b>Chemical Resistance</b>	Generally good resistance to acids, alkalis and oils at normal temperatures	

**Interpon**  
powder coatings  
EVERY COLOR IS GREEN

## Interpon 610 AM

<b>Pretreatment</b>	<p>Aluminium, steel or Zintec surfaces to be coated must be clean and free from grease. Iron phosphate and particularly lightweight zinc phosphating of ferrous metals improves corrosion resistance.</p> <p>Aluminium substrates may require a chromate conversion coating.</p>
<b>Application</b>	<p><b>Interpon 610</b> powders can be applied by manual or automatic electrostatic spray equipment. It is recommended that powder film thickness be between 60-110 microns. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.</p>
<b>Additional Information</b>	<p><b>Interpon 600 AM</b> in conjunction with Biocote Ltd ® has been tested for antimicrobial efficacy versus the ISO 22196: 2007 and exhibited a minimum of 95% and up to 99.99%v reduction in bacterial population, classified as 'microbiological results satisfactory'. Testing by Biocote Ltd ® is carried out by an independent laboratory and has included the following bacteria:</p> <p>Listeria monocytogenes Escheria coli 0157 Salmonella enteritidis Staphylococcus aureus (resistant strain) Bacillus subtilis Pseudomonas auruginosa Salmonella typhimurium Streptococcus faecalis Legionella pneumophila Enterbacter aerogenes</p> <p><b>Interpon 610HR</b> (High Reactivity) powders are also available in selected grades for use where a lower stoving temperature or shorter curing schedule is required.</p> <p><b>Sales code:</b> N-Series</p> <p><b>Stoving schedule:</b> 15 - 30 minutes at 160°C (object temperature) 8 - 16 minutes at 180°C</p> <p><b>Shelf life:</b> 12 months</p> <p>For further details on powder properties and film performance of <b>Interpon 610HR</b> please contact AkzoNobel.</p>
<b>Safety Precautions</b>	<p>Please consult the Material Safety Datasheet (MSDS)</p>

### FOR PROFESSIONAL USE ONLY

**IMPORTANT NOTE** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel